



## Francesca Silver

**Size:** 600X600 mm | **Design:** Marble | **Finish:** Glossy Finish in Vitrified SST Body | **Series:**



Front View



Scale View

## Packaging Details

Size	No. of tiles in box	Coverge Area	
		sq/mtr	sq/ft
600X600 mm	4.0	1.44	15.5

## Technical Specification

Sr.No.	Properties	CEN Code	Standard Test Method	ISO 13006:2018 Specification BIa	Nitco's Value
1	Deviation in Length %	EN 98	ISO 10545 - 2	$\pm 0.3$ % (Max $\pm 1.0$ mm)	$\pm 0.1$ %
2	Deviation in Thickness %	EN 98	ISO 10545 - 2	$\pm 5.0$ % ( Max $\pm 0.5$ mm )	$\pm 5.0$ %
3	Straightness of Edge %	EN 98	ISO 10545 - 2	$\pm 0.3$ % ( Max $\pm 0.8$ mm )	$\pm 0.10$ %
4	Diagonal Variation %(Rectangularity) Surface flatness	EN 98	ISO 10545 - 2	$\pm 0.3$ % ( Max $\pm 1.5$ mm )	$\pm 0.10$ %
5	a. Centre curvature b. Edge curvature c. Warpage	EN 98	ISO 10545 - 2	$\pm 0.4$ % ( Max $\pm 1.8$ mm )	$\pm 0.20$ % $\pm 0.20$ % $\pm 0.20$ %
6	Surface Quality	EN 98	ISO 10545 - 2	Min 95% free from any visible defects	Min 95% free from any visible defects
7	Water Absorption % By WT.	EN 99	ISO 10545 - 3	$< 0.5$	$< 0.08$
8	Breaking Strength, N	EN 100	ISO 10545-4	Min. 700 N	Min. 1000 N
9	Modulus of Rupture in N / mm <sup>2</sup>	EN 100	ISO 10545 -4	$> 35$	$> 35$
10	Thermal Shock Resistance	EN 104	ISO 10545 - 9	No Visible Defects	Resistant
11	Chemical Resistance (Except HF Acid)	EN 106	ISO 10545 - 13	No Visible Effect	No Visible Effect
12	Resistance To Stain		ISO 10545 - 14	Manufacture To State Class	Resistant
13	MOH Scratch Hardness	EN 101		Min 5	5
14	Gloss Value			Min 60	$> 70$